



INSTRUCTIONS FOR

USING WHITE OPAQUD LIQUID + Z-ETCH(ZIRFACE, ZIRCONIA BONDING SOLUTION)



Apply white or white plus liquid just once on the inner surface of zirconia crown. Do not apply an excessive amount



Dry for 15minutes at 200°C



Unlike white liquid, do not apply it as if you were brushing it on, but apply it by pressing it firmly to make sure there are no gaps. If you are not sure, search 'zirface' on youtube.



Sinter without a drying process